

# Uvijet KO



Uvijet KO inks are exclusively designed for the Acuity HD 2504.

## Features

- Conventional UV ink system
- Fast cure for high production output
- Excellent inter-coat lay down for backlit and solid prints
- Intense colours. Wide colour gamut
- Ultra low print odour
- Wide adhesion range
- Recommended for both internal and external applications
- Suitable for decoration of uneven substrates
- Suitable for use on the Acuity HD 2504 from Fujifilm

## Uvijet KO Ink Properties

The Uvijet KO range is a high quality UV curable inkjet system, for Piezo Drop-on-Demand print heads, specifically developed for use with the Acuity HD 2504 printer. The inks offer superb dot reproduction, lightfast bright colors, and adhere to a wide range of rigid and flexible uncoated materials.

## Uvijet KO Color Range

KO215 Cyan  
 KO052 Yellow  
 KO004 Black  
 KO867 Magenta

Available in 2 Litre sealed pouches.

QV017 UV Flush  
 ZE680 Adhesion Promoter  
 ZE720 Adhesion Master

Available in 1 Litre containers

## Application Range

Uvijet KO inks are formulated specifically to maximise the benefits of Fujifilm's Acuity HD2504 UV curing printers. These printers accept rigid and flexible materials up to 48mm thick and Uvijet KO inks are designed to decorate a wide range of uncoated media, including:

Media type	Adhesion Characteristic
Display Board	✓✓✓
Corrugated Board	✓✓✓
Foam Centred Board	✓✓✓
Foam PVC	✓✓✓ improves over 24 hrs
Acrylic	✓✓ (A) will improve adhesion to ✓✓✓
Flexible PVC	✓✓✓
Self Adhesive PVC	✓✓✓
Gloss Rigid PVC	✓✓ improves over 24 hrs
Fluted Polypropylene	✓ (B) will improve adhesion to ✓✓✓
Polyethylene	✓✓ (B) will improve adhesion to ✓✓✓
Paper	✓✓✓
Polycarbonate	✓
Polyester - Top Coated	✓✓
Digital Dibond	✓✓

Excellent ✓✓✓ Good ✓✓ Fair ✓

A = ZE680 Adhesion Promoter may optimise performance

B = ZE720 Adhesion Master may optimise performance

**THE END USER MUST DETERMINE SUITABILITY OF THIS PRODUCT FOR THE INTENDED USE PRIOR TO PRODUCTION.**

## Curing

Excellent cure and adhesion are achieved immediately on curing. However, maximum adhesion, chemical, scuff and scratch resistance may not be obtained until 24 hours after initial curing.

The actual level of cure will depend upon ink thickness, substrate and the UV curing lamps being used. Superior through cure may be obtained by reducing the print speed to increase the overall UV dose.

## Pre-production Tests

Uvijet KO ink is formulated to adhere to most major brands of plastic, polypropylene and polyethylene materials with a surface energy level of 42 dynes/cm or higher. For certain applications where finishing prints may require cutting, drilling or routing, it is recommended that a Uvijet Adhesion promoter is used prior to printing to aid adhesion and mechanical performance. However, it is strongly recommended that all substrates are tested before a commercial run.

## Plastics

Certain synthetics may be impregnated with lubricants which, like plasticisers, migrate impairing adhesion and block resistance for a considerable period after printing. There may also be surface contamination from residue of glues and adhesives from backing sheets. These can be overcome by wiping the surface with isopropyl alcohol (IPA) before printing.

To reduce the risk of problems generated by the build-up of static electricity it is advisable to pass an earthed anti-static brush over the material prior to printing. Allow static generated from protective sheets to dissipate before printing. Ensure that the printer is cited as per recommended humidity/temperature recommendations 30-70% RH, 18-30°C.

## Chemical and Abrasion Resistance

Uvijet KO inks have good chemical and excellent abrasion resistance. However for optimum resistance over- varnishing with a durable UV screen varnish such as Uvibond UV383 is recommended.

**SERICOL**  
 More than ink... Solutions.

**FUJIFILM**

PRODUCT INFORMATION

## Outdoor Use

Accelerated weathering tests have been carried out in a Xenon Arc Weatherometer set to the SAEJ1960 standard. Under these conditions the accelerated weathering of Uvijet KO inks equates to approximately 24 months outdoor exposure in a temperate climate, such as in Northern Europe. For polyethylene materials such as Correx, it is recommended that Uvijet Adhesion Master ZE720 is applied prior to printing to maximise outdoor weather resistance.

## Storage

Uvijet KO ink should not be stored in direct sunlight or near heat sources and should be kept away from peroxides. In the interest of maximum shelf-life storage temperatures should be between 5°C and 30°C. When stored in a cool environment the inks are expected to have a shelf-life of 6 months from date of manufacture.

## Fujifilm Sericol UK Limited:

- Has certification to the International Environmental Standard, ISO 14001.
- Is committed to minimising the risk to users of our products, and also to minimising the impact of our activities on the environment, from formulation through to production and supply.
- Research & development team, work to an in house Health, Safety and Environmental policy, termed 'Design for Health, Safety and Environment', with the aim of proactively developing products with the least impact on health, safety and the environment.
- Regularly review and monitor our impacts and activities, setting objectives and targets as part of a continual improvement process.
- Is committed to reducing waste through better use of raw materials, energy, water, re-use and recycling.

## Safety and Handling

### Uvijet Inks

- Have a flashpoint greater than 55°C and are therefore not classified as "dangerous substance" under the Dangerous Substances and Explosive Atmospheres Regulations (DSEAR).

Comprehensive information on the safety and handling of Uvijet inks is given in the appropriate Sericol Safety Data Sheets.

## Environmental Information

### Uvijet KO Inks

- Do not contain ozone-depleting chemicals as described in the Montreal Convention.
- Are formulated free from aromatic hydrocarbons.
- Are free of any volatile solvent and can therefore be considered to have less impact on the environment, when compared with solvent-based products.

### Uvijet Adhesion Promoter - ZE680

- Does not contain ozone-depleting chemicals as described in the Montreal Convention.
- Is formulated free from aromatic hydrocarbons.

### Uvijet Adhesion Master - ZE720

- Does not contain ozone-depleting chemicals as described in the Montreal Convention.

*The information and recommendations contained in this Product Information sheet, as well as technical advice otherwise given by representatives of our Company, whether verbally or in writing, are based on our present knowledge and believed to be accurate. However, no guarantee regarding their accuracy is given as we cannot cover or anticipate every possible application of our products and because manufacturing methods, printing stocks and other materials vary. For the same reason our products are sold without warranty and on condition that users shall make their own tests to satisfy themselves that they will meet fully their particular requirements. Our policy of continuous product improvement might make some of the information contained in this Product Information sheet out of date and users are requested to ensure that they follow current recommendations.*

**SERICOL**  
More than ink... Solutions.

**FUJIFILM**

FUJIFILM SERICOL UK LIMITED

Pysons Road Broadstairs Kent CT10 2LE United Kingdom  
Tel: (01843) 866668 Fax: (01843) 872184

**UK Sales** Tel: (01992) 782619 Fax: (01992) 782602  
Email: [uksales@fujifilmsericol.com](mailto:uksales@fujifilmsericol.com)

**Customer Service Centres** Tel: 0845 084 89 89



### Export Sales

Pysons Road Broadstairs Kent CT10 2LE United Kingdom  
Tel: +44 (0)1843 866668 Fax: +44 (0)1843 872122  
Email: [exportsales@fujifilmsericol.com](mailto:exportsales@fujifilmsericol.com)

[www.fujifilmsericol.com](http://www.fujifilmsericol.com)

PRINTED IN ENGLAND 2498/P7